

RFI 123

Project: COOLEY LABORATORY RENOVATION
Job: 3146 COOLEY LAB, PPA# 10-0023
Customer: STOFMT MSU BOZEMAN
Issued To: CONSTRUCTION MANAGEMENT SERV.
P.O. BOX 7274
BOZEMAN, MT 59715

POTENTIAL IMPACTS
Cost Impact: Yes
Schedule Impact: No

Attention: DONALD J. PLATISHA
Phone/Fax: 406 585-0611 / 406 585-2698

Coordination copies to:

Item: PAINTING OF SOFFITS Type: ARCH/STRUC
Reference: FC-C/A0.6 Spec. Section:
Attachments:

Description of Request

QUESTION:
The specified primer "Galvite Paint Alkyd Gloss" for exterior zinc coated metals is not sticking to the deck soffit . The painter has also tried using a direct to metal primer as recommended by the Sherwin Williams Paint this primer is also not sticking to the deck soffit. What primer should be used to paint the deck soffit?

Respond By: 05/28/12 By: TIM THOLT

Response

The paint data sheet for Galvite gives the required surface preparation: SSPC-SP1 which is defined in the S-W technical literature as solvent cleaning.

Very often there is an oil coating on galvanized sheet metal. The question should be directed to the roof metal supplier so that they can confirm what the coil was coated with to insure the proper solvent is used for cleaning/preparation.

Signed: Frank di Stefano Date: 5/23/2012

Proceed as Indicated: _____ Date: _____

Owner Authorized Representative